

DuPont™ Thermx® PCT

high performance polyester resin

Thermx® CG023 NC010

Thermx® CG023 NC010 is a 20% glass fiber reinforced polycyclohexylenedimethylene terephthalate resin for injection molding.

Property	Test Method	Units	Value
Identification			
Resin Identification	ISO 1043		PCT-GF20
Part Marking Code	ISO 11469		>PCT-GF20<
Mechanical			
Stress at Break	ISO 527	MPa (kpsi)	100 (14.5)
Strain at Break	ISO 527	%	2.3
Tensile Modulus	ISO 527	MPa (kpsi)	6400 (930)
Flexural Modulus	ISO 178	MPa (kpsi)	5800 (840)
Flexural Strength	ISO 178	MPa (kpsi)	155 (22.5)
Notched Izod Impact Strength	ISO 180/1A	kJ/m ²	6
Notched Charpy Impact Strength	ISO 179/1eA	kJ/m ²	6
Unnotched Charpy Impact Strength	ISO 179/1eU	kJ/m ²	35
Thermal			
Deflection Temperature 1.80MPa	ISO 75f	°C (°F)	250 (482)
Melting Temperature 10°C/min	ISO 11357-1/-3	°C (°F)	285 (545)

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.
 ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.
 Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Thermx® are trademarks or registered trademarks of DuPont Company. Copyright© 2005.

051215/051215

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-50102.

Thermx® CG023 NC010

Property	Test Method	Units	Value
Electrical			
Surface Resistivity	ASTM D 257	ohm	1E17
Volume Resistivity	ASTM D 257	ohm cm	1E15
Dielectric Strength, Short Time 500 V/s, 3.2mm	ASTM D 149	kV/mm (V/mil)	19.7 (500)
Dielectric Constant	ASTM D 150		
1E3 Hz			3.1
1E5 Hz			3.1
1E6 Hz			3.1
Dissipation Factor	ASTM D 150		
1E3 Hz			0.003
1E5 Hz			0.011
1E6 Hz			0.011
Other			
Density	ISO 1183	kg/m ³ (g/cm ³)	1380 (1.38)
Hardness, Rockwell Scale M	ASTM D 785		72
Processing			
Melt Temperature Range		°C (°F)	295-310 (565-590)
Melt Temperature Optimum		°C (°F)	300 (570)
Mold Temperature Range		°C (°F)	80-120 (175-250)
Mold Temperature Optimum		°C (°F)	100 (210)
Drying Time, Dehumidified Dryer		h	4-6
Drying Temperature		°C (°F)	95 (200)
Processing Moisture Content		%	<0.03

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.
 ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.
 Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Thermx® are trademarks or registered trademarks of DuPont Company. Copyright© 2005.

051215/051215

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-50102.